



Material weight Steel Tubes / Materialvikt Stål Rör, kg/m

Theoretical calculated weight / Teoretisk uträknad vikt

Use for Chrom moly, Docol R8, Mild Steel and other Steel Tubes.

Inch Tubes

	mm	0,50	0,80	0,89	1,24	1,47	1,65	2,11	2,41	3,05	4,78	6,35
mm	inch	0.020"	0.031"	0.035"	0.049"	0.058"	0.065"	0.083"	0.095"	0.120"	0.188"	0.250"
50,8	2"	0,632	1,005	1,115	1,549	1,825	2,038	2,579	2,933	3,656	5,521	7,090
44,45	1-3/4"	0,552	0,877	0,973	1,351	1,590	1,775	2,242	2,548	3,170	4,759	6,077
41,27	1-5/8"	0,512	0,813	0,902	1,252	1,473	1,643	2,074	2,356	2,927	4,378	5,571
38,1	1-1/2"	0,472	0,750	0,831	1,152	1,355	1,512	1,906	2,163	2,684	3,997	5,065
34,92	1-3/8"	0,432	0,686	0,760	1,053	1,238	1,380	1,738	1,971	2,441	3,617	4,558
33,34	1-5/16"	0,412	0,654	0,725	1,003	1,179	1,314	1,654	1,874	2,319	3,426	4,305
31,75	1-1/4"	0,393	0,622	0,689	0,954	1,120	1,248	1,570	1,778	2,198	3,236	4,052
30,16	1-3/16"	0,373	0,590	0,654	0,904	1,062	1,182	1,486	1,682	2,076	3,045	3,798
28,57	1-1/8"	0,353	0,558	0,618	0,854	1,003	1,117	1,402	1,586	1,954	2,855	3,545
25,4	1"	0,313	0,494	0,547	0,755	0,885	0,985	1,233	1,393	1,711	2,474	3,039
22,22	7/8"	0,273	0,431	0,476	0,656	0,768	0,853	1,065	1,201	1,468	2,093	2,532
19,05	3/4"	0,233	0,367	0,406	0,557	0,650	0,722	0,897	1,008	1,225	1,712	2,026
15,88	5/8"	0,193	0,303	0,335	0,457	0,533	0,590	0,729	0,816	0,982	1,331	1,519
12,7	1/2"	0,153	0,239	0,264	0,358	0,415	0,458	0,561	0,624	0,739	0,951	1,013
11,11	7/16"	0,133	0,207	0,228	0,309	0,357	0,392	0,477	0,527	0,617	0,760	0,760
9,52	3/8"	0,113	0,175	0,193	0,259	0,298	0,327	0,393	0,431	0,496	0,570	0,506
7,94	5/16"	0,093	0,143	0,157	0,209	0,239	0,261	0,309	0,335	0,374	0,379	0,253
6,35	1/4"	0,073	0,112	0,122	0,160	0,180	0,195	0,225	0,239	0,253	0,189	-

Profile Tubes

1" x 1-3/4"							1,757					
-------------	--	--	--	--	--	--	--------------	--	--	--	--	--

Millimeter Tubes

mm	0,5	1	1,5	2	2,5	3	3,5	4	4,5	5
14	0,170	0,327	0,471	0,603	0,722	0,829	0,923	1,005		
16	0,195	0,377	0,546	0,703	0,848	0,980	1,099	1,206	1,300	1,382
20	0,245	0,477	0,697	0,904	1,099	1,281	1,451	1,608	1,752	1,884
22	0,270	0,528	0,772	1,005	1,225	1,432	1,627	1,809	1,978	2,135
25	0,308	0,603	0,885	1,156	1,413	1,658	1,890	2,110	2,317	2,512
30	0,371	0,728	1,074	1,407	1,727	2,035	2,330	2,612	2,883	3,140
32	0,396	0,779	1,149	1,507	1,853	2,185	2,506	2,813	3,109	3,391
35	0,433	0,854	1,262	1,658	2,041	2,412	2,769	3,115	3,448	3,768
38	0,471	0,929	1,375	1,809	2,229	2,638	3,033	3,416	3,787	4,145
40	0,496	0,980	1,451	1,909	2,355	2,788	3,209	3,617	4,013	4,396
42	0,521	1,030	1,526	2,010	2,481	2,939	3,385	3,818	4,239	4,647
45	0,559	1,105	1,639	2,160	2,669	3,165	3,649	4,120	4,578	5,024
50	0,597	1,181	1,752	2,311	2,857	3,391	3,912	4,421	4,917	5,401

ME Racing Service AB

Svetsgränd 10
781 72 Borlänge
Sweden

e-mail: mail@meracing.com
www.meracing.com

Tel: +46 243 100 66
Fax: +46 243 211 412